

**Инструкция по замене перламутров 077 линии
на перламутры 051 линии
в рецептах из онлайн-базы Rock Paint**



Перейдите по ссылке <http://www4.rockpaint.co.jp/New/MixE/index.html#8>

ROCK COLOR MIXING DATA

ROCK PAINT CO. LTD. Color Mixing Formula Inquiry System

Go To ROCK PAINT Home Page

Introducing

- Color Code Locations
- Entering the Color Code (Japanese Cars)
- Entering the Color Code (NON-Japanese Cars)
- Entering the Color Code (Others)
- Site Policy

Automotive Refinishing Paints

- Color Mixing Formula
- Update information
- Entering the approximate calculation

QR code created with various data

DOWNLOAD version download

Go To Top

Color Code Search Automotive Refinishing Paints

(* mark required field)

Paint Type: 077LINE PRO TOUCH

Car Manufacturer: > Japanese > NON-Japanese > Others

Color Code: [input field]

Requested quantity: 1000 g ml / Usage Total

SEARCH CLEAR

Set this page as default

Copyright © 2011 ROCK PAINT All Rights Reserved.

1. Выберите линию автоэмалей
2. Выберите марку авто*
3. Введите код краски
4. Нажмите SEARCH (ПОИСК)

* Вводить марку автомобиля необязательно. Многие марки заключили соглашение о сотрудничестве в сфере покраски, поэтому один и тот же код используется при окраске автомобилей разных производителей. Например, в концерн General Motors входят Opel, Chevrolet, Holden, Daewoo. Идентичные коды многих красок имеют марки:

- KIA и HYUNDAI
- Nissan и Renault
- Mitsubishi, Peugeot и Citroen

ROCK PAINT Co., Ltd. / ROCK PAINT Co., Ltd. / www4.rockpaint.co.jp/New/MixE/index.html#15

aboutblank zvezda-em - Яд... Катировки Новости Рекомензуемые с... форум Primkiter.r... Расшифровка бур... Ретро и новое - Р... Другие закладки

Search Result List

ROCK PAINT CO. LTD. Color Mixing Formula Inquiry System

Select Checked SELECT ALL CLEAR Back to Search Page

Prev 10 items 1 2 Next 10 items (13 items)

Select	Car Manufacturer	Color Code	Color Name	First Year	Car Type	HBC	
<input type="checkbox"/>	NISSAN	KAK-0	COOL IRON (PM)	2008	SERENA	0 3	SELECT
	NTK No.	Handy	Color Type	Color Group	Image		
	2008-130	2008	M/P	GRAY			
<input type="checkbox"/>	NISSAN	KAK-1	COOL IRON (PM)	2008		0 3	SELECT
	NTK No.	Handy	Color Type	Color Group	Image		
	2008	M/P	GRAY		Actual Car		
ALL DIRECTIONS ARE SOMEWHAT RED HUE UNIVERSAL PEARL BASES ARE USED IN THIS FORMULA							
<input type="checkbox"/>	NISSAN	KAK-1	COOL IRON (PM)	2008		0 3	SELECT
	NTK No.	Handy	Color Type	Color Group	Image		
	2008	M/P	GRAY		Actual Car		
ALL DIRECTIONS ARE SOMEWHAT RED HUE							
<input type="checkbox"/>	NISSAN	KAK-2	COOL IRON (PM)	2008		0 3	SELECT
	NTK No.	Handy	Color Type	Color Group	Image		
	2008	M/P	GRAY		Actual Car		
ALL DIRECTIONS ARE BLACK. UNIVERSAL PEARL BASES ARE USED IN THIS FORMULA.							

Этот рецепт разработан с использованием перламутров 077 линии.

Этот рецепт разработан заново, с использованием перламутров 051 линии.

Выберите требуемый вариант и нажмите кнопку SELECT

Color Mixing Formula

[Back to Search Page](#)

[PRINT](#)

[Back to List Page](#)

Car Manufacturer	NISSAN
Color Code	KAK-2
Color Name	COOL IRON (PM)
Car Type	
Parts	BODY
First Year	2008

NTK No	
Handy	2008
Color Group	GRAY
Color Type	M/P
HBC	O 3
Rank	D



[Comment](#)

ALL DIRECTIONS ARE BLACK.

◆ 077LINE PRO TOUCH

Select a Paint Type [Help](#)

Product No.	Product Name	Mixing Amount	
		%	g
077L 4009	STAR METALLIC COARSE	56.85	568.5
077L 0234	BLACK	20.07	769.2
077L 0072	LAKE BLUE	7.63	845.5
077L 0030	TINTING BLACK	5.35	899.0
077L 0310	PEARL BASE 3B	5.02	949.2
077L 0048	MAGENTA	2.07	969.9
077L 0316	PEARL BASE G	0.67	976.6
077L 0095	FLAT BASE	2.34	1000.0
Total		100.00	1000.0

[Comment](#)



Requested Quantity

1000 g Usage ml Total

Нажмите на треугольник для выбора нового перламутра из 051 линии.
После нажатия весь рецепт будет пересчитан.

Color Mixing Formula

ROCK PAINT CO. LTD. Color Mixing Formula Inquiry System

[Back to Search Page](#)

[PRINT](#)

[Back to List Page](#)

Color Name: COOL IRON (PM)
Car Type:
Parts: BODY
First Year: 2008

Color Group: GRAY
Color Type: M/P
HBC: 0 3
Rank: D



[Comment](#)

ALL DIRECTIONS ARE BLACK.

◆ 077LINE PRO TOUCH

Select a Paint Type [Help](#)

Product No.	Product Name	Mixing Amount	
		%	g
077L 4009	STAR METALLIC COARSE	58.53	585.3
077L 0234	BLACK	20.66	791.9
077L 0072	LAKE BLUE	7.86	870.5
077L 0030	TINTING BLACK	5.51	925.6
077L P150	BLENDING CLEAR P	1.71	942.7
051L 4310	U.PEARL BASE 3B	1.71	959.8
077L 0048	MAGENTA	2.13	981.1
077L 0316	PEARL BASE G	0.69	988.0
077L 0095	FLAT BASE	1.20	1000.0
Total		100.00	1000.0



Requested Quantity:

1000

g Usage
 ml Total

[Comment](#)

This data is a rough calculation.
Please mix a little and check the color.

Если нужно заменить
оба перламутра,
нажмите на
треугольник второго
перламутра.

При полном пересчете формула выглядит так

ROCK PAINT Co., Ltd. / www4.rockpaint.co.jp/New/MixE/index.html#16

Color Mixing Formula

ROCK PAINT CO. LTD. Color Mixing Formula Inquiry System

[Back to Search Page](#) [PRINT](#) [Back to List Page](#)

Color Name	COOL IRON (PM)	Color Group	GRAY
Car Type		Color Type	M/P
Parts	BODY	HBC	O 3
First Year	2008	Rank	D

[Comment](#)

ALL DIRECTIONS ARE BLACK.

◆ 077LINE PRO TOUCH

Select a Paint Type [Help](#)

Product No.	Product Name	Mixing Amount	
		%	g
077L 4009	STAR METALLIC COARSE	58.67	586.7
077L 0234	BLACK	20.71	793.8
077L 0072	LAKE BLUE	7.87	872.5
077L 0030	TINTING BLACK	5.52	927.7
077L P150 ▲	BLENDING CLEAR P	1.94	947.1
051L 4310 ▲	U.PEARL BASE 3B	1.71	964.2
077L 0048	MAGENTA	2.14	985.6
051L 4316 ▲	U.PEARL BASE G	0.23	987.9
077L 0095	FLAT BASE	1.21	1000.0
Total		100.00	1000.0

[Comment](#)

This data is a rough calculation.
Please mix a little and check the color.



Requested Quantity

1000 g Usage
 ml Total